

AMERDRAIN® 300/350

PREFABRICATED SHEET DRAIN

americanwick.com




PRODUCT OVERVIEW

AMERDRAIN 300/350 prefabricated sheet drains are designed with a 30,000 psf core to meet your most demanding horizontal application design loads. Our dimple core design offers significantly higher flow rates and better protection to waterproofing membranes than geonets.

AMERDRAIN 300 is constructed using a nonwoven filter fabric for standard soil applications. AMERDRAIN 350 incorporates a high strength woven monofilament filter fabric to create a strong bridge to eliminate intrusion of the fabric under load. Woven filter fabrics are better suited to receive concrete pours and provide excellent filtration for the organic soils used in planter applications.

AMERDRAIN 300/350 products are typically recommended for plaza decks, parking decks, split slab construction and planter applications.



PACKAGING

- » 4' x 50' Rolls
- » 6 Rolls per pallet

TECHNICAL DATA			300	350
Physical Properties	ASTM Test Method	Unit of Measure	Typical Value	Typical Value
FABRIC				
Material ¹			PP	PP
Water Flow Rate	D-4491	gpm/ft ²	165	160
		Lpm/m ²	6,724	6,520
Grab Tensile Strength	D-4632	lbs	100	410 x 220
		N	445	1,824 x 979
Puncture Resistance	D-4833	lbs	65	105
		N	289	467
Apparent Opening Size	D-4751	sieve	70	45
		mm	0.21	0.35
Grab Elongation	D-4632	%	65	15
UV Resistance	D-4355	% / 500 Hrs	70	90
CORE				
Material ¹			HIPS	HIPS
Thickness	D-1777	in	0.25	0.25
		mm	6.35	6.35
Compressive Strength	D-1621	psf	30,000	30,000
		kPa	1,436	1,436
Installed Horizontal Flow Rate ²	D-4716	gpm/ft	2.6	2.6
		Lpm/m	32	32
Maximum Flow Rate ²	D-4716	gpm/ft	13	13
		Lpm/m	161	161
Recycled Content			79%	67%
<small>1 - PP = Polypropylene; HIPS = High Impact Polystyrene 2 - Flow rates tested @ 3600 psf (172 kPa) compressive load. Installed horizontal flow with concrete sand overburden tested at a hydraulic gradient of 0.05. Maximum in-plane flow rate tested at a hydraulic gradient of 1.0</small>				

All information, drawings and specifications are based on the latest product information available at the time of printing. Constant improvement and engineering progress make it necessary that we reserve the right to make changes without notice. All physical properties are typical values unless otherwise stated. Standard variations in mechanical properties of 10% and in hydraulic properties of 20% are normal.



1209 Airport Road, Monroe, NC 28110
 TF 800.242.WICK • PH 704.238.9200
 FX 704.238.0220 • info@americanwick.com

